



BAYSEAL™ 2.7

*Division 7-Thermal and Moisture Protection
Closed-Cell Roofing Foam System
ESR-1221*

Product Description

Bayseal 2.7 is a two-component, closed-cell spray-applied polyurethane foam system. Bayseal 2.7 SPF offers high compressive strengths, smooth aesthetics and a broad application temperature window.

The Bayseal 2.7 system is self flashing and provides seamless protection by sealing cracks, crevices and holes while insulating decks from temperature extremes. Bayseal 2.7 SPF offers a high R-value and can reduce condensation when applied correctly, thus reducing the possibility of mold growth, enhancing energy efficiency, and lowering lifecycle costs by providing a low maintenance deck solution.

Unique Properties

The Bayseal 2.7 spray polyurethane foam system comprises an “A” component, which is a polymeric diisocyanate, and a “B” component, which is a combination of polyols, additives, and HFC-245fa blowing agent.

Recommended Uses

Roofing Systems Agricultural Applications
Tank Insulation Air Barrier Systems

As with any product, use of foam made with the Bayseal 2.7 system must be tested (including, but not limited to, field testing) in advance by the user to determine suitability.

Typical Physical Properties*

Properties	Test Method	Value
R Value (aged):	ASTM C-518	6.4 at 1 inch
Compressive Strength:	ASTM D-1621	45 psi (nominal)
Core Density:	ASTM D-1622	2.7 lbs./ft ³ (nominal)
Closed Cell Content:	ASTM D-2856	> 90%
Tensile Strength:	ASTM D-1623	80 psi
Water Absorption	ASTM D-2842	< 2%
Moisture Vapor Transmission:	ASTM E-96	1.0 perm-in
Dimensional Stability:	ASTM D-2126	% Change in Volume
7 days @ 158°F, 100% RH		< 5%
7 days @ 200°F, 100% RH		< 5%
7 days @ -20°F, 100% RH		< 5%
Surface Burning Characteristics	UL 723	Flame Spread Index < 75

* These items are provided as general information only. They are approximate values and are not part of the product specifications.

Environmental Consideration and Substrate Temperatures

Applicators must recognize and anticipate climatic conditions prior to application to ensure the highest quality foam and to maximize yield. Ambient air and substrate temperatures, moisture, and wind velocity are all critical determinants of foam quality and selection of the appropriate reactivity formulation. Variations in ambient air and substrate temperature will influence the chemical reaction of the two components, directly affecting the expansion rate, amount of rise, yield, adhesion and the resultant physical properties of the foam insulation.

To obtain optimum results, the Bayseal 2.7 system should only be spray-applied to substrates when ambient air and surface temperatures fall within the range of 45°F and 120°F. All substrates to be sprayed must be dry at the time of application. Moisture in the form of rain, fog, frost, dew, or high humidity (>85%R.H.), will react chemically with the mixed components, adversely affecting the polyurethane foam formation, dimensional stability and physical properties of the finished product. Wind velocities in excess of 12 miles per hour may result in excessive loss of exotherm and interfere with the mixing efficiency, affecting foam surface, cure, and physical properties and will cause overspray. Precautions must be taken to prevent damage to adjacent areas from overspray.

Processing Parameters and Physical Characteristics	
Pre-heater Temperature:	"A" and "B" 120-135°F
Hose Temperature:	"A" and "B" 120-135°F
Pressures:	1000-1500 psi (dynamic)*
Mix Ratio Parts:	1 to 1 by volume "A" to "B"
Viscosity at 70°F	500-650 cps "B" Component 150-250 cps "A" Component
Shelf Life	6 months @ 65°F to 80°F

* Dependent upon hose length.

Product Reactivity

Processing Designation	Surface Temperature
Winter	45 - 65°F
Regular	55 - 80°F
Summer	Above 75°F

* Note: Adhesion should not be tested within one hour of application.

Storage Conditions

Store drums at 70°F to 80°F for a minimum of 48 hours before use. Materials in containers should be maintained at 65°F to 85°F while in use. Conditioned trailers or tanks may be necessary. Material temperature should be confirmed with a thermometer or an infrared gun. Do not configure equipment to recirculate Bayseal 2.7 components from proportioner back into drum. Do not recirculate or mix other suppliers' "A" or "B" component into Bayseal 2.7 system containers.

CAUTION: If components are below suggested temperatures, the increased viscosity of the components may cause pump cavitation resulting in unacceptable SPF application. If components are above suggested temperatures, there may be loss of blowing agent resulting in diminished yield.

Processing Equipment

2:1 transfer pumps are recommended for material transfer from container to the proportioner. The plural component proportioner must be capable of supplying each component within $\pm 2\%$ of the desired 1:1 mixing ratio by volume. Hose heaters should be set to deliver 125°F to 135°F materials to the spray gun. These settings will ensure thorough mixing in the spray gun mix chamber in typical applications. Optimum hose pressure and temperature will vary with equipment type and condition, ambient and substrate conditions, and the specific application. It is the responsibility of the applicator to properly interpret equipment technical literature, particularly information that relates to the acceptable combinations of gun chamber size, proportioner output, and material pressures. The relationship between proper chamber size and the capacity of the proportioner's pre-heater is critical. Mechanical purge spray guns (specifically direct impingement or DI type) are recommended for highest foam quality.

CAUTION: Extreme care must be taken when removing and reinstalling drum transfer pumps so as NOT to reverse the "A" and "B" components.

Per Lift Application

Applicators should apply a maximum pass thickness of 2 inches, with a minimum of 30 minutes between passes.

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling materials used to produce foam from the Bayseal 2.7 system. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets and product labels. More resources are available at spraypolyurethane.com, polyurethane.org, spray-foam.org, baycareonline.com, or by contacting the Bayer MaterialScience Product Safety and Regulatory Affairs Department in Pittsburgh, PA.

Note: The information contained in this bulletin is current as of January 2012, please contact Bayer MaterialScience to determine whether this publication has been revised.

Bayer MaterialScience LLC

100 Bayer Road • Pittsburgh, PA 15205-9741 • Phone: 1-800-662-2927 • www.spf.bayermaterialscience.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Sales Offices

2400 Spring Steubner Road West, Spring, TX 77389 • 1-800-221-3626 • Fax: 1-281-288-6450
