



Roof Surface/System Cross Reference Chart
CONCRETE

SYSTEM	WARRANTY LENGTH	GAL/SQ	BASE COAT	GAL/SQ	INTERMEDIATE COAT	GAL/SQ	INTERMEDIATE COAT	GAL/SQ	TOP COAT	GAL/SQ	TOTAL DFT
Ure-A-Max (Hybrid)	10 years	1	Aromatic Urethane 520	1.25	Aromatic Urethane 520	1.25	Aliphatic Urethane 510-CA		Aliphatic Urethane 510-CA	1.25	38
	15 Years	1	Aromatic Urethane 520	1.5	Aromatic Urethane 520	1.5	Aliphatic Urethane 510-CA		Aliphatic Urethane 510-CA	1.5	45
	20 Years	1	Aromatic Urethane 520	1.5	Aromatic Urethane 520	1.25	Aliphatic Urethane 510-CA	1.25	Aliphatic Urethane 510-CA	1.5	55
Ure-A-Sil	12 years	1	Aromatic Urethane 520	1.25	Aromatic Urethane 520	1.25	—	—	Silicone 410	1.25	38
									High-Solids Silicone 412	.9	
	15 years	1	Aromatic Urethane 520	1.5	Aromatic Urethane 520	1.5	—	—	Silicone 410	1.5	45
									High-Solids Silicone 412	1.1	
	20 years	1	Aromatic Urethane 520	1.5	Aromatic Urethane 520	1.5	Silicone 410	1.25	Silicone 410	1.25	55
									High-Solids Silicone 412	1.8	
Ure-A-Sil California	12 years	1	Aromatic Urethane 512-CA	1.25	Aromatic Urethane 512-CA	1.25	—	—	High-Solids Silicone 412	.9	38
	15 years	1	Aromatic Urethane 512-CA	1.5	Aromatic Urethane 512-CA	1.5	—	—	High-Solids Silicone 412	1.1	45
	20 years	1	Aromatic Urethane 512-CA	1.5	Aromatic Urethane 512-CA	1.5	High-Solids Silicone 412	.9	High-Solids Silicone 412	.9	55

Refer to application guidelines for detailed installation instructions. Adhesion tests are required for all roof restoration projects.

* Depending on the condition of the existing roof system, a primer may not be necessary. Contact American WeatherStar technical services for more information.

DFT = Dry Film Thickness