



Application Guideline URE-A-SIL ROOF RESTORATION SYSTEM OVER CONCRETE

To ensure warranty eligibility, each job must be approved by American WeatherStar before it begins.

PART 1 - GENERAL

1.01 DESCRIPTION

- A. The intention of this guideline is to outline the procedures for the application of American WeatherStar reflective roof coatings for the purpose of coating **STRUCTURAL CONCRETE DECK ROOFS** and **OTHER CONCRETE SURFACES**. These suggested guidelines describe materials, methods, and conditions necessary for the proper application of the American WeatherStar roof coating system. Actual application requirements may vary and are the responsibility of the contractor.
- B. This guideline may not outline all procedures for preparation and finishing of penetrations, drains, flashings, etc. This work should be outlined separately by the contractor before the work commences and shall be performed observing good trade practices.

1.02 APPROVED APPLICATOR

All American WeatherStar products shall be applied by a single, experienced and competent contractor approved by American WeatherStar.

PART 2 - PRODUCTS

2.01 COATINGS AND RELATED MATERIALS

All materials used shall be manufactured by and or approved by WeatherStar Coatings and shall meet the following specifications:

2.02 ELASTOMERIC COATING SYSTEM

AROMATIC URETHANE 520

Type: Single-component moisture cure urethane
Viscosity: 2000 cps
Elongation: 350% \pm 50%
Tensile strength: 975 \pm 25 psi
Volume solids: 69% \pm 2%
Color: Silver

SILICONE 410

Type: UV resistant elastomeric
Viscosity: 6,000 \pm 1000 cps
Elongation: 318%
Tensile strength: 500 psi
Volume solids: 69% \pm 2%
Color: White, gray, or tan

URETHANE BRUSH-GRADE 522

Type: Single-component urethane flashing material
Viscosity: 30,000-40,000 cps
Elongation: 350% \pm 50%
Tensile strength: 975 \pm 25 psi
Volume solids: 69% \pm 2%
Color: Silver

HIGH SOLIDS SILICONE 412

Type: UV resistant elastomeric
Elongation: 170% \pm 25%
Tensile strength: 450 \pm 50 psi
Volume solids: 92% \pm 2%
Color: White, gray, and tan

POLYESTER FABRIC

Type: Spunbound polyester
Viscosity: N/A
Tensile strength: 35 psi

ECOCLEANER 925

Type: Surface Cleaner
VOC: 0 grams/liter
Color: Clear

SBS PRIMER 950

Type: Primer/surface conditioner
Viscosity: 250 \pm 150 cps
Color: Black or gray



2.03 DELIVERY AND STORAGE

- A. Materials shall be delivered in their original, tightly sealed containers or unopened packages, all clearly labeled with the manufacturer's name, file number, and lot numbers.
- B. Materials shall be stored out of the weather in their original tightly sealed containers or unopened containers as recommended by the manufacturer.

2.04 WARRANTY

- A. American WeatherStar warrants that the material supplied will meet or exceed physical properties as published. The contractor guarantees that workmanship will be free of defects in coating application. Since performance of existing roof substrate or previously applied coatings are beyond the control of American WeatherStar or the contractor, requests for additional warranty coverage shall be subject to prior approval by American WeatherStar.
- B. Comply with manufacturer's warranty application procedures. A Pre-Project Inspection Report should be submitted and approved prior to job commencement.

PART 3 - INSTALLATION

3.01 SURFACE PREPARATION

- A. Preparation shall include all requirements specified by American WeatherStar to ensure proper adhesion of the American WeatherStar products to the substrate. (An adhesion test may be necessary.)
- B. Preparation shall include, but not be limited to the following:
 - 1. All unnecessary and non-functional equipment and debris shall be removed from the roof.
 - 2. Substrate must be pressure-washed. A minimum working pressure of 3,000 psi shall be used to remove all dirt, dust, previous paints and coatings which are delaminating as well as waste products (oil, oil-based roof cements, solvents, grease, animal fats, etc). If necessary, use **ECOCLEANER 925** to remove all contaminates. Contact American WeatherStar for additional information.
 - 3. HVAC condensate drains shall be properly routed to roof drains or plumbed off of the roof.
 - 4. Wet roof insulation and damaged membranes are to be removed and replaced as necessary to match existing specified material.
 - 5. All roof penetrations, curbs, vent stacks and related roof penetrations are to be flashed in accordance with roof manufacturer's specifications.
 - 6. All laps and wall flashings are to be repaired in accordance with roof manufacturer's specifications.
 - 7. Contractor shall make every effort to mechanically eliminate all ponding water areas on the roof surface prior to application of any roof coating product.

3.02 PRIMER APPLICATION

- A. Examine substrate to receive roof coating. Do not proceed with installation of the American WeatherStar roof coating system until all problem areas have been corrected in a manner acceptable to the manufacturer.
- B. In order to seal porous concrete, the roof substrate may be primed with **SBS PRIMER 950** at a rate of 100 square feet per gallon. Contact American WeatherStar for additional information or substitute primer.

3.03 PREPARATION FOR COATING

- A. All seams, penetrations, curbs, and parapet walls are to be flashed using **URETHANE BRUSH-GRADE 522**.



Application Guideline
**URE-A-SIL ROOF RESTORATION SYSTEM
OVER CONCRETE**

1. Seams: Apply a layer of **URETHANE BRUSH-GRADE 522** into each seam. (Min 30mils DFT)
 - a. Apply **URETHANE BRUSH-GRADE 522** at a rate of 50 wet mils.
 - b. Application shall be a minimum of 3" wide over the seam and feathered on to the existing roof membrane.
2. Penetrations: Apply **URETHANE BRUSH-GRADE 522** at a rate of 90 wet mils. (Min 60mils DFT)
 - a. Application shall encapsulate the area around the penetration
 - b. Application shall extend a minimum of 3" on to the existing roof membrane.
 - c. Feather the application so as to not cause water damming.
3. Parapet Walls: Apply **URETHANE BRUSH-GRADE 522** to all seams and flashings on parapet walls.
 - a. Seams: Apply a layer of **URETHANE BRUSH-GRADE 522** into each seam. (Min 30mils DFT)
 1. Apply **URETHANE BRUSH-GRADE 522** at a rate of 50 wet mils.
 2. Application shall be a minimum of 3" wide over the seam.
 - b. Flashings: Apply a layer of **URETHANE BRUSH-GRADE 522** at flashing points. (Min 60mils DFT)
 1. Apply **URETHANE BRUSH-GRADE 522** as required to seal any existing flashings at a rate of 90 wet mils.
 2. Application should be made to insure water tightness of the flashing detail.
- B. Repair all cracks and splits in the roof using **URETHANE BRUSH-GRADE 522** in the same manner as each seam is repaired.
 1. Cracks or splits less than 1/4"
 - a. Apply a layer of **URETHANE BRUSH-GRADE 522** into each crack or split.
 - b. Apply **URETHANE BRUSH-GRADE 522** at a maximum rate of 100 wet mils.
 - c. Multiple pass may be required for deep cracks
 - d. Application shall extend a minimum of 3" wide over the crack and feathered on to the existing roof membrane.
 2. Cracks or splits greater than 1/4"
 - a. Apply a layer of **URETHANE BRUSH-GRADE 522** into each crack or split.
 - b. Apply **URETHANE BRUSH-GRADE 522** at a maximum rate of 100 wet mils.
 - c. Multiple pass may be required for deep cracks
 - d. Application shall extend a minimum of 3" wide over the crack and feathered on to the existing roof membrane.
 - e. Once crack is filled and leveled with existing roofing membrane, apply suitable width **POLYESTER FABRIC** as to extend 2" on either side of the crack.
 - f. Once fabric is embedded, encapsulate with **AROMATIC URETHANE 520**.
 3. If cracks predominate the existing roofing membrane, an American WeatherStar Full-Fabric System may be required.

Note: Please refer to the Detail Drawing for Three Course Fabric options on A & B above. Please call American WeatherStar for assistance if needed.



Application Guideline
**URE-A-SIL ROOF RESTORATION SYSTEM
OVER CONCRETE**

3.04 APPLICATION RATES

A. 12 Year System Requirement (38 mil Urethane-Silicone System)

1. **Base Coat:** Apply base coat of **AROMATIC URETHANE 520** roof coating at a rate of 1.25 gallons per 100 square feet.
2. **Intermediate Coat:** Apply an intermediate coat of **AROMATIC URETHANE 520** roof coating at a rate of 1.25 gallons per 100 square feet.
3. **Top Coat:**
 - o **Standard Option:** Apply coat of **SILICONE 410** at a rate of 1.25 gallons per 100 square feet
 - o **High Solids Option:** Apply coat of **HIGH SOLIDS SILICONE 412** at a rate of .9 gallons per 100 square feet.
4. **Granules (Optional):** Immediately broadcast roofing granules into finish coat at the rate of 30 lbs. per 100 square feet.

B. 15 Year System Requirement (45 mil Urethane-Silicone System)

1. **Base Coat:** Apply base coat of **AROMATIC URETHANE 520** roof coating at a rate of 1.5 gallons per 100 square feet.
2. **Intermediate Coat:** Apply an intermediate coat of **AROMATIC URETHANE 520** roof coating at a rate of 1.5 gallons per 100 square feet.
3. **Top Coat:**
 - o **Standard Option:** Apply a top coat of **SILICONE 410** at a rate of 1.5 gallons per 100 square feet.
 - o **High Solids Option:** Apply a top coat of **HIGH SOLIDS SILICONE 412** at a rate of 1.1 gallons per 100 square feet.
4. **Granules (Optional):** Immediately broadcast roofing granules into finish coat at the rate of 30 lbs. per 100 square feet.

C. 20 Year System Requirement (55 mil Urethane-Silicone System)

1. **Base Coat:** Apply base coat of **AROMATIC URETHANE 520** roof coating at a rate of 1.5 gallons per 100 square feet.
2. **Intermediate Coat:** Apply an intermediate coat of **AROMATIC URETHANE 520** roof coating at a rate of 1.5 gallons per 100 square feet.
3. **Intermediate Coat:**
 - o **Standard Option:** Apply coat of **SILICONE 410** at a rate of 1.25 gallons per 100 square feet
 - o **High Solids Option:** Apply coat of **HIGH SOLIDS SILICONE 412** at a rate of .9 gallons per 100 square feet.
4. **Top Coat:**
 - o **Standard Option:** Apply coat of **SILICONE 410** at a rate of 1.25 gallons per 100 square feet
 - o **High Solids Option:** Apply coat of **HIGH SOLIDS SILICONE 412** at a rate of .9 gallons per 100 square feet.
5. **Granules (Optional):** Immediately broadcast roofing granules into finish coat at the rate of 30 lbs. per 100 square feet.

Note: A single coat of **HIGH SOLIDS SILICONE 412** is permissible at 1.8 gallons per one hundred square feet.



Application Guideline
**URE-A-SIL ROOF RESTORATION SYSTEM
OVER CONCRETE**

- D. Each coat must be allowed to dry for 24-48 hours depending on humidity and temperature. The roof is to be inspected for defects, flaws or holidays and repaired if necessary.
- E. Each contractor should estimate coating requirements based on actual experience and needs to figure in losses due to applicator experience, surface texture, wind, waste, and other factors that can affect gallons required.
- F. It is the applicator's responsibility to verify wet and dry mil thickness during the application process to ensure proper dry mil thickness of the total roofing system.

3.05 PONDING

- A. Known ponding water areas are to be repaired using commonly acceptable roofing practices so as to allow proper drainage of roof area.
- B. Ponding water areas are a sign of possible mechanical failure in the roof.
- C. Ponding water is NOT excluded from the warranty of the Ure-A-Sil roof restoration system when properly installed by an American WeatherStar Approved Contractor.

3.06 RESTRICTIONS/LIMITATIONS

This system is to be used only in conjunction with commonly accepted roofing standards but not limited to the following:

- A. No application of materials shall commence during inclement weather or when precipitation is imminent.
- B. No thinning of materials is permitted.
- C. No materials are to be applied to wet, dirty, or frozen surfaces.
- D. In conjunction with the final inspection, all debris, containers, materials and equipment are to be properly removed from the job site. Grounds are to be cleaned, undamaged, and acceptable to the owner.
- E. Reflectivity of coatings may be reduced if roof surface is not cleaned on a regularly scheduled basis.

Caution: Do not apply within two hours of sunset, rain, fog or freezing temperatures. The American WeatherStar roof coating system must be completely dry before exposing to water or foot traffic. Keep American WeatherStar containers covered when not in use. Dispose of all containers in accordance with state and local environmental regulations. Keep away from children. If ingested, DO NOT induce vomiting. Call physician immediately.