



Roof Surface/System Cross Reference Chart **METAL**

SYSTEM	WARRANTY LENGTH	PRIMER	GAL/SQ	BASE COAT	GAL/SQ	INTERMEDIATE COAT	GAL/SQ	TOP COAT	GAL/SQ	TOTAL DFT
Met-A-Gard	5 years	Red Oxide Rust Prime 912*	.5	Acrylic 211	.75	—	—	Acrylic 211	.75	10
	10 years	Red Oxide Rust Prime 912*	.5	Acrylic 211	1	—	—	Acrylic 211	1	15
Met-A-Gard+	12 years	Red Oxide Rust Prime 912*	.5	High-Tensile Acrylic 211	1.25	—	—	High-Tensile Acrylic 211	1.25	20
	15 years	Red Oxide Rust Prime 912*	.5	High-Tensile Acrylic 211	1.5	—	—	High-Tensile Acrylic 211	1.5	25
	20 years	Red Oxide Rust Prime 912*	.5	High-Tensile Acrylic 211	1.25	High-Tensile Acrylic 211	1.25	High-Tensile Acrylic 211	1.25	30
Met-A-Sil	12 years	Red Oxide Rust Prime 912*	.5	Silicone 410	1	—	—	Silicone 410	1	20
	15 years	Red Oxide Rust Prime 912*	.5	Silicone 410	1.25	—	—	Silicone 410	1.25	25
	20 years	Red Oxide Rust Prime 912*	.5	Silicone 410	1.5	—	—	Silicone 410	1.5	30
Met-A-Sil (High-Solids Option)	12 years	Red Oxide Rust Prime 912*	.5	High-Solids Silicone 412	.75	—	—	High-Solids Silicone 412	.75	20
	15 Years	Red Oxide Rust Prime 912*	.5	High-Solids Silicone 412	.9	—	—	High-Solids Silicone 412	.9	25
	20 Years	Red Oxide Rust Prime 912*	.5	High-Solids Silicone 412	1.1	—	—	High-Solids Silicone 412	1.1	30

SYSTEM	WARRANTY LENGTH	PRIMER	GAL/SQ	BASE COAT	GAL/SQ	INTERMEDIATE COAT	GAL/SQ	INTERMEDIATE COAT	GAL/SQ	TOP COAT	GAL/SQ	TOTAL DFT
Color-Gard	10 years**	Red Oxide Rust Prime 912*	.5	High-Tensile Acrylic 211	1.25	—	—	High-Gloss Acrylic 215	.4	High-Gloss Acrylic 215	.4	20
	15 years**	Red Oxide Rust Prime 912*	.5	High-Tensile Acrylic 211	1.25	High-Tensile Acrylic 211	1.25	High-Gloss Acrylic 215	.4	High-Gloss Acrylic 215	.4	25
	20 years**	Red Oxide Rust Prime 912*	.5	High-Tensile Acrylic 211	1.5	High-Tensile Acrylic 211	1.5	High-Gloss Acrylic 215	.4	High-Gloss Acrylic 215	.4	30
**COLOR-GARD SYSTEM IS COVERED BY A 10-YEAR COLOR FADE WARRANTY.												

Refer to application guidelines for detailed installation instructions. Adhesion tests are required for all roof restoration projects.

* Depending on the condition of the existing roof system, a primer may not be necessary. Contact American WeatherStar technical services for more information.

DFT = Dry Film Thickness